



### APPLICATIONS /

- Adhesive mortar white of fine layer for tiling of sandstone in interior coating.

### SUPPORTS /

- On traditional plaster, prefabricated of plaster, mortar...

### APPLICATION RECOMMENDATIONS /

- Application temperature 5°C to 30°C
- Respect the mixing water.
- The tiles should be of medium absorption (>3%) on plaster.
- It Left joints of minimum 2 mm , filled with **Pavicolor** Fine Joint, Thick Joint or Flexible.

## Conventional adhesive mortar

### CEMCOL SPECIAL PLASTER

#### DESCRIPTION /

Cement, selected aggregates and limestone, organic and inorganic additives

#### COMMENTS /

- Do not apply on supports with moisture higher than 4%.
- Avoid placement on old dead plaster or weak plaster.
- For placement of ceramic parts of low absorption it recommends to use **Cemcol Porcelanic**.
- In very absorbent paraments, it recommends to wet before and make a first layer of 2 mm with the same bonding mortar.
- Do not apply the tile, stone, marble... in form of "touches".

#### USE CHARACTERISTICS /

- Rest time after mixing: 5 minutes
- Correction time approximated: 30 minutes
- Life paste: 2-3 hours approx.

\*These times may vary considerably depending on room temperature.

#### FEATURES /

- Mixing water: 24.0%
- Mass density: 1600 kg/m<sup>3</sup>
- Water retention: 99.0%
- Initial adhesion:  $\geq 0.5$  N/mm<sup>2</sup>
- Adhesion after immersion:  $\geq 0.5$  N/mm<sup>2</sup>

\* These results have been obtained in standard conditions and may vary depending on conditions of placing.



**CEM COL**  
**WITHOUT UNSTUCK**  
**CONVENTIONAL**

#### EXECUTION TERMS /

- The support must be resistant and be completely setting and free of dust, oil, grease....
- Clean up the loose parts.
- Use mesh between supports of different nature.
- In very absorbent supports or exposed to sun it recommends to wet before.

#### PRODUCT

### CEM COL SPECIAL PLASTER

#### Conventional adhesive mortar

- On plaster or plasterboard
- For tiles and sandstone
- Good adhesion

#### HOW TO USE /



Mixing **Cemcol Special Plaster** with 6/ 7 litres of clean water per bag of 25 kg until obtain a homogeneous and smooth mass.

- Make the mixture with low mixer.
- Let rest 5 minutes.



Extend the material with notched trowel in small sections (maximum 2m<sup>2</sup>).



Place the tiles by pressing and moving up and down until get the crushing of the bonding mortar.

Before place the ceramic check that the adhesive mortar has not formed a surface film this will avoid it adhesion. If so, pass again the notched trowel.

#### PRESENTATION/

Paper bag of 25 kg moisture-proof  
 Pallets of 1200 kg (48 bags)



#### COLORS /

White

#### Yield /

3-4 kg/m<sup>2</sup>

\*These consumption may vary depending on the placement.

#### STORAGE /

12 months since manufacture date in original closed container and shelter form weather.

#### REFERENCES /

\*Low absorption: Absorption less than 3%

\*Medium absorption: Absorption between 3-10%

\*High absorption: Absorption higher than 10%