



APPLICATIONS /

- To obtain surfaces architecturally disable of exposed aggregated.
- The absence of solvent facilitates its use.
- It's not necessary to protect the extremes the surfaces to be treated with exception of painted facades and porous supports.

FINISH /

- Aggregated exposed

RECOMMENDATIONS OF APPLICATION /

- Application temperature 5-30°C
- Do not apply if there are standing water on the surface of the fresh concrete.
- To obtain good results, it's important get good homogenization.
- A very strong vibration of the concrete, producing risk of driving up the finer elements causing a separation of the mixture.

**Surface deactivating
(aggregated exposed)**

FILMAT-RD

DESCRIPTION /

Surface deactivating for concrete, aggregated exposed finish, in aqueous base.

OBSERVATIONS /

- The quantity of fine inert that contains the concrete influences on the final aesthetic aspect final.
- Is recommended the use of polypropylene fibbers to increase the cohesion to deactivate.
- **Very important**, before start the work, make a preliminary test on the concrete to be used later in production, in order to verify if the desired effect is achieved.

USE CHARACTERISTICS /

- Apply **Filmat-RD** uniform mode
- The concrete will be cleaned with pressure water (100-150 bares).
- The operator shall keep the nozzle between 20-40 cm from the concrete surface
- Strong wind or sun exposure, wash within 12-15 hours after the application of the product.

*These times can vary considerably according weather temperature.

FEATURES /

- Nature: liquid
- Dynamic Viscosity to 20°C: <500 mPa.s
- PH: P01 to P03: 3 ± 1
P04 to P08: 9 ± 1





TESTS /

- The table below shows the possible variations related temperature.
- References are for information and depending on the type of cement, cement dosage, temperature...

REFERENCE	COLOR	DEPTH (In mm)	DIMENSIÓN AGGREGATE (mm)
Filmat RD 01	Rosa	Ácid	-
Filmat RD 02	Verde	-1	3 a 5
Filmat RD 03	Azul	-2	5 a 8
Filmat RD 04	Naranja	-3	8 a 10
Filmat RD 05	Salmón	-4	10 a 14
Filmat RD 06	Amarillo	-5	14 a 18
Filmat RD 07	Violeta	-6	18 a 25
Filmat RD 08	Rojo	-7	20 a 30

*These results have been obtain in standard conditions and may vary depending on the conditions of placing.

HOW TO USE /



Apply with spray **Filmat-RD** over the fresh concrete surface and uniformly approximately 6-8 m²/kg of product.



Between 5-24 hours (under attack) remove the surface product with a pressuring water machine (20-40 cm distance from concrete).



Once the surface is dry (24-48 hours), apply curing resin **Racly 2/ Orfapol 50**.

PRODUCT

FILMAT-RD

Surface deactivating (aggregated exposed)

- Concrete finish of aggregated exposed
- Street furniture
- Highways barriers in concrete exposed
- Easy application

PRESENTATION/

Can of 18 kg
Pallets de 648 kg (36 can)

COLORS /

Colorless.

YIELD /

6 – 8 m²/kg of product.

STORAGE /

12 months since date manufacture, in original closed container, and shelter from weather.

