



APPLICATIONS /

- Colored Micro-mortar of high features for swimming pools, concrete walls...indoor and outdoor.
- In walls and roofs
- Minimum thickness (1-2 mm)

SUPPORTS /

On concrete, concrete walls, rough coating with **Revistamp Sec**, gresite, glazed tile...

APPLICATION RECOMMENDATIONS /

- Respect always the same percentage of **Acrylcem** during the mixture.
- Do not add water to the product.
- Respect the joints of expansion and retraction.
- Application temperature 5°C to 35°C
- Do not apply with risk of freeze, direct sunstroke, strong wind or rain.

Micro-mortar for coating and renewal of swimming pools and walls

MICRO-MORTAR PAVICEM 2 mm THICKNESS

DESCRIPCIÓN /

Special cement, mineral load, additives, resins and pigments.

COMMENTS /

- Do not add water or any other additive to the mortar
- In absorbent or porous surfaces wet before apply the product.
- Treat the singular areas (fissure...) with fiberglass mesh.
- Do not apply directly on brick cladding, block concrete...

*Dry time will vary depending on the temperature and existing moisture.

USE CHARACTERISTICS /

- Mixture life: 3 hours
- Open time: 2 hours
- Maximum thickness: 0.1-2 mm
- Maximum thickness by layer: 0.5-1 mm
- Hard to the touch: 4-6 hours
- Put into service: ≥ 28 days

*These times can vary considerably depending on temperature.

FEATURES /

- Mass density: 1.1 g/ cm³
- Adhesion : 0.98 N/mm²
- Abrasion wear: 14.5 mm
- Water absorption by capillary: 0.003 g/cm²
UNE- EN 13748-2

* These results has been obtained in standard conditions and may vary depending on conditions of placement





EXECUTION CONDITIONS /

- The base of plaster prior to receiving the **Pavicem** micro-mortar must have good flatness, be strong and absorbent.
- Before applying the micro-mortar **Pavicem**, we recommend that the base mortar, concrete or self-leveling be completely setting (≥ 28 days).
- Apply a first layer of **Pavicem Grueso Especial Piscinas** to regularize the surface.
- On concrete paraments these should be plains and clean without trace of grout, release agents...

HOW TO USE /



The proportion of the mixture will be of 2 to 1.(2 parts of **Pavicem** by 1 part of **Acrylcem** approx.).

Mix with mixer at low speed, until a homogeneous mass workable and smooth.



1) Apply a first regularization layer with **Pavicem Grueso Especial Piscinas**.

2) Apply with the appropriate trowel at a rate 0.5 mm by layer to achieve the desired effect.



Once dry the surface (≥ 28 days) apply 1-2 coats of cured polyurethane **Orfapol-Incoloro** (special for swimming pools).

PRODUCT

MICRO-MORTAR PAVICEM 2 mm THICKNESS

Micro-mortar for swimming pools coating and renewal

- Colored continuous coating
- Without joints
- Deformable and flexible
- Impermeable and breathable
- High features
- Indoor and outdoor

PRESENTATION/ Packing 1-5-15 kg

Plastic can of 15 kg.

Pallets of 405 kg (27 cans).

COLORS /

Colour chart of 56 colors.

(Others on request).

YIELD /

400 - 800 g/m²

*These consumption may vary depending on the support and number of coats.



STORAGE /

12 Months since date manufacture, in original closed container and shelter from weather.