



**APPLICATIONS /**

- High Chemical resistance
- For pools protection
- Brightness unchanged
- Interior and exterior

**SUPPORTS /**

- **Pavicem** Micro-mortar, concrete, Mortars,
- **Pavistone** Thematic stone, terrazzo, ceramic...

**APPLICATION RECOMMENDATIONS /**

- The base must be completely dry and free from damp
- Respect always the same dosage
- Do not add any additive to the mix
- Temperature to apply: 10-25°C

**Aliphatic polyurethane paint**

**ORFAPOL INCOLORO**

**DESCRIPTION /**

Finish paint of polyurethane base of two components

**RESISTANCE CHART /**

**(Immersion testing)**

Hydrochloric Acid 10 and 20%	500 hours	Unchanged
Sulphuric Acid 10 and 20%	500 hours	Oxide. On set.
Distilled water	8 months	Unchanged
Sodium Chloride 3.5%	8 months	Unchanged
Sodium Hydroxyde 20%	15 days	Unchanged
Ammonia	3 months	Regular
Acetate Isobutyl	8 months	Unchanged
White Spirit	6 months	Good
Salt Fog 5% sodium chloride and 37-38 °C	8 months	Unchanged
Environment: Humidity 100% and 40°C	3 months	Good

**USE CHARACTERISTICS /**

- Work stoppages: 8 hours
- Hard to the touch: 60 min.
- To repainting: 8 hours approx.
- Total drying: 24 hours

\*These times can vary considerably depending on room temperature.

**FEATURES /**

- Specific weight: 1.2 g/cm<sup>3</sup>
- Viscosity: 25 °C: 100-120 seconds.
- Aspect: Paint
- Mixing proportion by weight:  
Resin: 66.6%  
Hardener: 33.4%

\*These results are from test standard and may vary depending on the conditions of placing



## ORFAPOL INCOLORO

### EXECUTION CONDITIONS /

In all cases it is indispensable to the application on dry, clean and free of liens and other materials.

- Do not paint when wet.
- On **Pavicem** cement based surfaces, concrete, mortar... it must be completely set ( $\geq 28$  days) and moisture-free.

### HOW TO USE /



- Homogeneously mixing the two components.
- The low viscosity of **Orfapol Incoloro**, allowed to be applied in pure form.



Application by roller, brush or spray.

- With gun, after dilution with 10% maximum of thinner TP.
- Interval between layers: 4-12 hours

### PRODUCT

## ORFAPOL INCOLORO

### Polyurethane paint

- Porcelain effect
- To protect pools
- Based cement pavement
- Excellent mechanical resistance
- Permanence of color

### PRESENTATION /

Containers of 1 and 5 kg  
(2 components)

### COLORS /

Colourless

### YIELD /

1 kg between 10-14 m<sup>2</sup> (1 layer)

### STORAGE /

6 months since manufacture date in original closed container and shelter form weather.