

## POINTING OF CERAMIC



### APPLICATIONS /

- Flexible Mortar for joint filled between tiles from 3-30 mm, in any kind of pavement, coating ceramic or **Revistamp E**.
- Indoor and outdoor.
- Radiant heat floor.
- For joints exceeding to 30 mm, the dough will be more consistency.

### APPLICATION RECOMMENDATIONS /

- Application temperature 5°C to 30°C
- The mixing will be equal to the consistency of a cement color
- Respect always the same portion of water, the excess water will difficult the cleaning, also the final finish.
- Do not apply as grout.
- Avoid the application in rainy time or very moisture, with risk of freeze and sunstroke directly.

**Flexible mortar colored for joints from 3 to 30 mm.**

## PAVICOLOR - F (Flexible)

### DESCRIPTION /

Cement, selected aggregates, synthetic resins, organic additives and inorganic mineral pigments.

### COMMENTS /

- Fungicidal properties.
- Watertight joints
- Controlled retraction. (Pavicolor Plus)

### USE CHARACTERISTICS /

- Rest time after the mixing: 5 minutes.
- Maximum time of cleaning: 30-60 minutes.
- Mass life: 60 minutes.
- Hard to the touch: 1-2 hours.
- Put into service: 3-4 days.

\*These times can vary considerably depending on temperature.

### FEATURES /

- Powder density: 1.4 g/cm<sup>3</sup>
- Mixing water: 25%
- Capillary: 0.9 g/Dm<sup>3 min ½</sup>
- shrinkage: 1.50 mm/m

\* These results has been obtained in standard conditions and may vary depending on conditions of placement.



[www.pavistamp.com](http://www.pavistamp.com)

Customer Service: +34 902 158 743

POINTING OF CERAMIC

**PAVICOLOR - F**

FLEXIBLE

**EXECUTION CONDITIONS /**

- The joints between ceramic will be clean, dry and free of dust.
- The pointing should be realized 24-48 hours after fixation of the ceramic.
- In applications on porous or absorbent surfaces, realize a treatment of tiles with **Protector PAVISTAMP**, before realize the pointing to prevent stained the pieces.

**PRODUCT****PAVICOLOR - F (Flexible)****Flexible mortar colored for joints from 3-30 mm**

- Impermeable
- Flexible
- Fungicide
- Excellent adhesion
- Allow the mix between colors

**HOW TO USE /**

Mix **Pavicolor F** with 1.5 litres of clean water per bag of 5 kg. Manually or mechanically and let rest during 5 minutes.



Fill the joints between tiles. Wait 30-60 minutes to eliminate the product remains. Suitable for use with gun refillable.



Clean with a wet sponge and rinse with clean water until get the desired finishing touch.

**PRESENTATION/**

Bag of 5kg (in boxes of 20 kg)  
Pallets of 18 boxes (360 kg)

**COLORS /**

12 colors  
Other colors on request

**YIELD /**

Between 0,4 and 0,8 kg/m<sup>2</sup>

\*These consumption may vary depending on thickness and length of joints, as well as dimension of ceramic material.

**STORAGE /**

12 months since date manufacture in original closed container and shelter form weather.

