

POINTING OF CERAMIC



APPLICATIONS /

- Colored mortar for filled of joints till 3mm thickness between ceramic pieces and any kind of coating or pavement.
- Indoor and outdoor.

APPLICATION RECOMMENDATION /

- Application temperature 5°C to 30°C
- In joints less than 1.5 mm apply as grout
- Respect always the same proportion water, the excess of water will make difficult to clean, as well as the finishing touch.
- Avoid the application in rainy or damp weather, with risk of freeze, or hot weather.
- Do not add any kind of additive to the product.

Colored mortar for fine joint till 3 mm

PAVICOLOR - JF (fine joint)

DESCRIPTION /

Cement, selected aggregates, synthetic resins, organic additives and inorganic mineral pigments.

COMMENTS /

- In outdoor use **Pavicolor F** (flexible).
- For joints thicker than 3 mm use **Pavicolor JG**.
- For joints of **Revistamp E** use **Pavicolor JG**.

USE CHARACTERISTICS /

- Rest time after mixing: 5 minutes
- Maximum time for cleaning: 30-60 minutes
- Mass life: 60 minutes
- Put into service: 3-4 days

*These times can vary considerably depending on temperature.

FEATURES /

- Apparent powder density: $1 \pm 0.1 \text{ g/cm}^3$
- Mixing water: 35%
- Mass density: 1.6 g/m^3
- Capillary: $2 \text{ g/dm}^2 \cdot \text{min} \frac{1}{2}$

* These results has been obtained in standard conditions and may vary depending on conditions of placement



POINTING OF CERAMIC

PAVICOLOR JF
FINE JOINT**EXECUTION CONDITIONS /**

- The joints between ceramic will be clean, dry and free of dust.
- The pointing should be realized 24 – 48 hours after fixation of the ceramic.
- In applications on porous or absorbent surfaces, realize a treatment of tiles with **Protector PAVISTAMP**, before realize the pointing to prevent stained the pieces.

PRODUCT**PAVICOLOR - JF (fine joint)****Colored flexible mortar for fine joint till 3 mm**

- Excellent workability
- Without cracking
- Water resistant
- It allowed color mixture

HOW TO USE /

Mix **Pavicolor JF** with 1,7 litres of clean water per bag of 5 kg. Manually or mechanically and let rest during 5 minutes.



Fill the joints between tiles. Wait 30-60 minutes to eliminate the product remains. Clean with a wet sponge and rinse with clean water until get the desired finishing touch.

PRESENTATION /

Bag of 5kg (in boxes of 20 kg).
Pallets of 18 boxes (360 kg).

COLORS /

12 colors.
Other colors on request.

YIELD /

Between 0,2 y 0,6 kg/m²

*These consumption may vary depending on thickness and length of joints, as well as dimension of ceramic material.

STORAGE /

12 months since date manufacture in original closed container and shelter form weather.

