

REPAIR AND MOUNTING MORTAR



APPLICATIONS /

- Quick-setting mortar plug to stop waterways.
- Cracks, basements and warehouse.
- Even with high pressure.

MORTAR ANCHOR /

- For anchor fast.
- Pipes, gates, railings...

SUPPORTS ACCEPTED /

- Cementitious, concrete, concrete blocks
- Indoor and outdoor.

APPLICATION RECOMMENDATIONS /

- Application temperature 5°C and 30°C.
- Clean up the area to be sealed for free openings.
- Do not apply a risk of frost.
- In case of major leaks or high pressure, plug in successive phases.
- For preventive treatment wet abundantly the support.

Tapavias mortar and fast set anchor

PAVIFIX®

DESCRIPTION /

Special cement, selected aggregates, resin and additives of instant setting.

COMMENTS /

- Not suitable for filling big surfaces.
- Wear rubber gloves
- Do not resist cracking support

USE CHARACTERISTICS /

- Mixing time: less than 1 minute
- Start of setting: 0.5 to 1 min.
- Final setting: 1 to 3 min.
- Wait for lag: 24-48 hours.
- Thickness of application: 2 to 10cm.

* These times can vary considerably depending on ambient temperature

FEATURES /

- Powder density: 1.3 g/cm³
- Mixing water: 20-30%
- Bulk density: 1.8 g/cm³
- Fire behaviour: 1.8 g/cm³
- P.H.: 12

* These results were obtained in standard conditions and may vary depending on the placing.



www.pavistamp.com

Customer Service: +34 902 158 743



EXECUTION CONDICIONS /

- The supports must be clean up, stable, resistant and free of dust, grease, oils...
- Remove deteriorated concrete and cleaned up using mechanical chipping, until obtain a surface in good conditions to receive the **Pavifix**.
- In areas where you see the iron frame, clean with sandblast or wire brush and cover with mortar **Pavifer**.
- On very smooth or some absorbent applying in situ a quick primer of **F-300**.
- Humidify support before apply the mortar.
- Leaks or cracks should be opened at least a width and depth of 2-3 cm to form straight edges.
- Remove fragmented and poor in cement areas.
- Clean by pressure water or wire brush.

HOW TO USE /



Mix in small quantities, with hands protected by gloves.



To start the hardening of **Pavifix** (30 and 60 seconds) press the paste on the leak or fissure of water during a few minutes (1 to 5 min).



For anchors mix with 25-30% water until obtain a smooth homogeneous mass.

PRODUCT

PAVIFIX®

Tapavías mortar and fast set anchor

- Hydraulic mortar
- Fast setting in seconds
- Waterproof and resistant
- Free from chlorides
- No shrinkage
- It's skinnable

PRESENTATION /

Can of 5 kg.

COLORS /

Cement gray.

YIELD /

1.5-2 kg/m² and mm of thickness.

STORAGE /

6 months since manufacture date in original closed container and shelter from weather and moisture.

