

REPAIR AND MOUNTING MORTAR



APPLICATIONS /

- Waterproofing of concrete walls and structures subject to cracking phenomena.
- Waterproofing of showers, bathrooms, swimming pools... prior to placement of the ceramic coating.
- Rehabilitation of terraces and balconies, overhangs and terraces, roofs, cornices ... outdoors and exposed to significant temperature changes.
- It is usually a waterproof protective coating of surfaces exposed to the action of water and chemical aggression of external phenomena such as de-icing salts, sulphates, chlorides...

SUPPORTED ACCEPTED /

- Concrete, prefabricated concrete, plaster, ceramic...

APPLICATION RECOMMENDATIONS /

- Application temperature between 5-30°C
- Do not apply risk of rain, ice...
- In hot weather does not apply to full sun.
- Place the fiberglass mesh between the first and second layers on terraces and walls cracked.
- Minimum final thickness of 3-4 mm at all points.

Hydraulic mortar waterproof flexible

PAVIMPER

DESCRIPTION /

Special cement, selected aggregates, resins, additives and active ingredients

COMMENTS /

- Do not add any additive to the mortar.
- In trodden ground, the mortar.
- Resistant to aggressive and sea water contact.

USE CHARACTERISTICS /

- Rest time after mixing: 5 min.
- Mass life approx.: 1 hour.
- Application thickness by layer: minimum 2 mm.
- Start setting: 4 hours.
- Waiting time between coats: 4 hours.
- Wait for filling the tank: ≥ 28 days.
- Coating-paint: > 6 days.

*These times may vary considerably depending on conditions of room temperature

FEATURES /

- Bulk density: 1.3 g/cm³
- Paste Density: 1.6 g/cm³
- Determination of transversal deformation: 2.5 mm
- Waterproof DIN 1048: Waterproof
- Adhesion to concrete: 1.6 MPa

* These results were obtained in standard conditions and may vary depending on the placing.



www.pavistamp.com

Customer Service: +34 902 158 743

MORTAR
PAVIMPER
HYDRAULIC

EXECUTION CONDITIONS /

- The supports shall be clean up, without grout or concrete release.
- If necessary pressure washing with water or sand blasting, to ensure a perfect adherence.
- The support will have good flatness, without cracks or uneven areas.
- Repair all damaged areas (holes, voids...) **Pavigrout** repair mortar.
- Try singular points with suitable mesh.
- Wet the support before application.

HOW TO USE /

Mix one bag of **Pavimper** (25kg) with 5-6 litres of clean water until obtain a homogeneous mass.



Apply with brush a first layer about 2 kg/m² and let dry during 4-5 hours.

Apply a second coat, crossed the previous one and with the same consistency.



On walls or crack surfaces, between coats place fiberglass mesh.

PRODUCT**PAVIMPER**

Hydraulic mortar waterproof flexible

- Outdoor waterproofing
- Repair cracks and waterproof
- Fits on supports with small movements
- Does not change the drinking water
- A special machine
- Resistant to sea water

PRESENTATION /

Paper bags of 25 kg,
Moisture-proof.
Pallets of 1200 kg (48 Bags).

**COLORS /**

White and gray.

YIELD /

1.6 kg/m² and mm of thickness.

STORAGE /

12 months since manufacture date in original closed container and shelter.

