



Thick micro-mortar for preparing of floors and walls

PAVICEM GRUESO

DESCRIPTION /

Grey and white cement, arid in different grain sizes, additives and resins.

COMMENTS /

- Do not add water or any additive to the mortar.
- In absorbent or porous surfaces wet before apply the product.
- Treat the singular areas (fissures...) with fibreglass mesh.
- The time of dry vary according existing temperature and moisture.

USE CHARACTERISTICS /

- Mix life: 3 hours
- Open time: 2 hours
- Maximum thickness: 0.1-2 mm
- Maximum thickness by layer: 0.5-1 mm
- Dry to touch: from 5-7 hours
- Implementation: of 24 hours

*These times can vary considerable according the weather temperature.

FEATURES /

- Adhesion: EN-1015/12: 0.98 N/mm²
- Water absorption: 0.004 g/cm²
- Freeze-thaw: 0.01 kg/cm²

* These results were obtained in standard conditions and may vary depending on the conditions of placing.

APPLICATIONS /

- Thick Micro mortar grey and white for preparing floors and walls to receive the micro mortar **Pavicem**.
- Minimum thickness (0.1-0.2 mm)
- On concrete slab, porous concrete, marble, ceramic, wood,...

FINISHES /

- Preparation product

APPLICATION RECOMMENDATIONS /

- Respect always the same percentage of **Acrylcem** while mix.
- Do not add water to the product.
- Respect the joints of expansion and retraction.
- Application temperature 5°C to 35°C



MICRO-MORTAR
PAVICEM GRUESO
 2MM THICKNESS

EXECUTION CONDITIONS /

- The support should be resistant and be setting, clean, free from dust, paint, oil...
- Applying a first coat of **Pavicem Grueso** to stabilize the surface.
- In old concretes, mill the surface layer, eliminate all the puddles, apply 1-2 coats of consolidator **F-600**.
- On new concrete, this it has to be completely set (≥ 28 days).

HOW TO USE /

Mixing ratio will be of 2 to 1 (2 parts of **Pavicem Grueso** by 1 part of **Acrylcem** approximately).



Mix with the blender on slow speed until the mass is workable and smooth homogeneous.



One coat of **Pavicem Grueso** it's enough to plain the surface (in very irregular surfaces apply self-levelling **Pavifluid-5, 10 or 30 mm**).



Once the surface is plain, apply 1-2 coats of **Pavicem** until obtain the desire effect.

PRODUCT

PAVICEM GRUESO

Thick Micro-mortar for preparation of floors and walls

- Preparation to receive the **Pavicem**
- Pavements and walls
- Without joints
- Indoor and outdoor

PRESENTATION / Container 1-5-25 kg
 Plastic can of 25 kg
 Pallets of 675 kg (27 cans)



COLORS /
 White and gray
 Others, on request

YIELD /
 400 – 800 g/m²
 *These yields can vary according the support and number of coats.

STORAGE /
 12 months since the date of manufacture, in closed container and shelter from the weather.

REFERENCES /
 In floors with good flatness, marble, mortar or plain surfaces apply directly **Pavicem micromortero**.