



APPLICATIONS /

- Self-leveling mortar preparation and smoothing uneven surfaces, so before placing a light pavement.
- For new construction and rehabilitation.
- Indoors.

SUPPORTS /

- Concrete, mortar, terrazzo, ceramic...

THICKNESS /

- 2 to 10 mm.
- Type of finish:
Paints **Paviplast** (epoxy)
Carpet, hardwood...

APPLICATION RECOMMENDATIONS /

- Respect always the same percentage of water.
- Respect the minimum required thickness according support or local.
- Respect the expansion and fractionation joints
- Application temperature 5°C a 35°C

Self-levelling floor mortar fast set

PAVIFLUID-5

DESCRIPTION /

Cement, selected aggregates, fiber, additives, and inorganics.

COMMENTS /

- Do not add water or any other additive
- In absorbent surfaces wet before apply the product.
- Do not use on supports subject to continuous rising damp.
- Do not use for levelling outside
- Do not add water to the mixture that has already begun the process of set.
- Do not apply to industrial floor.

USE CHARACTERISTICS /

- Mixing time: 2-3 minutes
- Rest time before applying: 2 minutes
- Mass life : 20 minutes
- Hard to the touch: 3 to 5 hours
- Time to coating: 24-36 hours
- Time for sanding: from 24 hours
- For applying of paints the wait will be ≥ 15 days

*These times can vary considerably depending on room temperature.

FEATURES /

- Powder density: 1.4 g/cm³
- Mass density: 1.9 g/cm³
- Adhesion EN13892: 0.6 N/mm²
- Flexion: 2.3 N/mm²
- Compression: 6 N/mm²
- Hardness: 34 N/mm²
- Wear Bhôme: 21.1 cm³/50 cm²
- Testing UNE- EN 13813: 2003

* These results are from standard tests and may vary depending on the conditions of placing.



SELF-LEVELLING
PAVIFLUID-5
2-10 MM THICKNESS

EXECUTION CONDITIONS /

- The support must be solid and hard, dry, dust free, disintegrated areas, paints, waxes and oils, oxides, traces of plaster ...
- Cement based parties which are not solids should be eliminated or if possible enhance with consolidator **F-600**.
- On surfaces of anhydrite, very smooth or porous to apply before a bridge linking past **F-800** or **F-300** quick primer.
- In concrete cracked or degraded clean before applying the self-levelling **Pavifluid-5** with suitable mesh.
- On new concrete, it must be completely set ≥ 28 days.

PRODUCT

PAVIFLUID-5

Self-leveling floor mortar fast set

- Suitable for light pavement placement.
- In thicknesses of 2-10 mm.
- Pumpable
- Quick setting in service
- Good adhesion
- Indoors

HOW TO USE /



*For the mixing and for plastering with machine, the percentage will be 24-26%.

*Manual mixing:

1 bag of **Pavifluid-5** with 6 - 6,5 liters of water, until obtain a homogeneous and smooth mass.



*If its necessary smoothing out with a levelling float.

*Use the roller of prongs to eliminate the air from the product.

VERY IMPORTANT: For successive coats these will realize once the first coat get hard to the touch, without being total setting.

PRESENTATION /

Paper bags of 25 kg, moisture-proof.

Pallets of 1200 kg (48 bags)

COLORS /

Gray

Others on request

YIELD /

1.5 kg/m² and mm thickness

STORAGE /

12 months since manufacture date in original closed container and shelter from the weather

REFERENCES /

For thickness over 10 mm, use **Pavifluid-10**.

